

FLUID FILM® “AS” AEROSOL

MATERIAL SAFETY DATA SHEET

DATE PREPARED: 12/09

1. Identification of the Substance/Preparation & Supplier

Name of Supplier:

FOOD GRADE APPROVED

NLS Products

**Box 790, 1 Lakewood Crescent
Bobcaygeon, ON K0M 1A0**

Tel: (705) 738-2321 Fax: (705) 738-4550

Product Name: FLUID FILM® Aerosol “AS” (FOOD GRADE APPROVED)

Product Type: Liquid, Lubricant, and Corrosion Inhibitor

Product Stock #'s: 1450 (145 g), 3300 (333g) SC60 (60g Sample) Aerosol

2. Composition/Information on Ingredients

CONTAINS NO SOLVENTS, SILICONES, TEFLON OR KNOWN CARCINOGENS.

Product (less propellant)

Hazardous components:

CAS No.

Propane (propellant)

68-476-86-8

N Butane (propellant)

68-476-86-8

Petroleum Oil mist

64742-65-0

3. Hazards Information

Aerosol: Contents under pressure, 70 ± 5 PSIG

Eye Contact: May cause mild irritation.

Skin Contact: Prolonged contact could cause irritation.

Inhalation: Exposure in confined areas, without benefit of protective gear, may result in light-headedness and irritation to respiratory tract.

Ingestion: No information available.

4. First Aid Measures

Eye Contact: Flush with plenty of clean water for at least 15 minutes. If irritation persists, obtain medical attention.

Skin Contact: Wipe excess material from the skin with a cloth, followed by washing with soap and water. A waterless skin cleaner is beneficial in removing the material from the skin.

Inhalation: If respiratory symptoms develop, move victim away from source of exposure and into fresh air. If symptoms persist, seek medical attention.

Ingestion: If symptoms develop, seek medical attention.

Product Name: FLUID FILM® AEROSOL “AS”

Product Type: Liquid, Lubricant, and Corrosion Inhibitor

5. Fire Fighting Measures

Flammability: Flammable
Extinguishing Media: Extinguish with dry chemical, CO₂ or foam
Special Consideration: Aerosol – Contents under pressure, 70±5 PSIG. Fire fighters should enter area wearing positive pressure respiratory protection.

6. Accident Release Measures

Do not allow product to enter drains or watercourses. Transfer bulk of material into another container. Absorb remaining residue with proper absorbents such as earth or vermiculite. Sweep up and dispose of as solid waste in accordance with applicable regulations.

7. Handling and Storage

Storage Temperature: 0 to 49°C
Storage Precautions: No special requirements. Keep in closed containers.
Handling: Avoid contact with skin and eyes. Observe good standards of industrial hygiene.

8. Exposure Controls/Personal Protection

Engineering Measures: Provide forced air ventilation when applying in confined spaces.
Respiratory Protection: Use approved respirator with organic vapor cartridges.
Eyes: Chemical eye goggles.
Hands: Non-natural, non-butyl rubber gloves are recommended.
Skin: Use protective clothing. Remove contaminated clothing and wash the affected area with soap and water.
Exposure Limits: Not determined.

9. Typical Physical and Chemical Properties

Appearance: Straw colored liquid. **Odor:** Mild piney odor (less propellant).
Water Solubility: Not soluble. **PH Neat:** 7.8 **Specific Gravity (25°C):** 0.886 (less propellant).
Freezing Point: Not determined. **Vapor Pressure:** Not determined. **Boiling Point:** Not determined.
Flash Point: Propellant -91°C (Closed cup). AS (less propellant) 207°C (COC).

10. Stability and Reactivity

Stability: Stable under normal conditions. Hazardous polymerization will not occur.
Hazardous Decomposition Products: Combustion can produce a variety of compounds including oxides of sulfur, oxides of carbon, water vapor and unidentified organic and inorganic compounds, some of which may be toxic.
Conditions to Avoid: Exposed flames, high temperature sources and strong oxidizers.
Product Name: FLUID FILM® AEROSOL "AS"
Product Type: Liquid, Lubricant, and Corrosion Inhibitor

11. Toxicological Information

LD50 (Animal/Oral): Product (less propellant) – Greater than 14 Grams/Kilogram

Health Effects:

Eyes: Minimally irritating.

Skin: Prolonged contact could cause skin irritation.

Inhalation: Excessive exposure due to lack of protective gear or proper ventilation could result in pulmonary abnormalities.

Ingestion: Ingestion of this product is not regarded as a significant health hazard likely to arise in normal use.

12. Ecological Information

No data available.

13. Disposal Recommendations

Product should be disposed of via authorized waste disposal contractors in accordance with all local and national regulations.

14. Transportation Information

Consumer commodity, ORM-D. Non-hazardous, non-regulated.

15. Regulatory Information

Safety Phrases: KEEP OUT OF REACH OF CHILDREN.

16. Other Information

Do not mix with other chemicals.

This data sheet does not constitute an assessment of the workplace risks as required under the provisions of the Health & Safety at Work act and the Control of Substances Hazardous to Health (COSHH).

Legal Disclaimer: The information supplied above is based upon the present state of our knowledge of the product at the time of publication. It is given in good faith and no warranty is implied with respect to the specification or quality of the product. The user must satisfy himself that the product is entirely suitable of his purpose.

NLS Products

**Box 790, 1 Lakewood Crescent
Bobcaygeon, ON CANADA K0M 1A0**

**Tel: (705) 738-2321 Fax: (705) 738-4550
www.nlsproducts.ca**

FLUID FILM "AS" AEROSOL

DATE PREPARED: 06/05

PRODUCT DATA "AS" # 207 TECHNICAL BULLETIN & MSD SHEET

FOOD GRADE APPROVED

NATIONAL STOCK NUMBERS

STOCK # 570	57g CARDED 12/CTN. AEROSOL "AS":	
STOCK # 850	57g 24/CTN. AEROSOL "AS":	
STOCK # 1450	145g 12/CTN. AEROSOL "AS":	
STOCK # 3300	333g 12/CTN. AEROSOL "AS":	8030-01-387-1131
STOCK # PC354	354 ml 12/CTN. NON-AEROSOL PUMP "NAS":	8030-01-381-6357
STOCK # 3700	3.5L 4/CTN. NON-AEROSOL BULK "NAS":	8030-01-386-3871
STOCK # 4300	20L PAIL NON-AEROSOL BULK "NAS":	8030-01-387-1070
STOCK # 4500	208L DRUM NON-AEROSOL BULK "NAS":	

FLUID FILM Aerosol (AS) and Bulk (NAS) meet and greatly exceed mil spec # C 16173 (Army/Navy), and mil spec # C 81309, C 85054 (Military Aviation). Boeing spec # MB0110-020.

FLUID FILM "AS" & "NAS" LUBRICANTS, PENETRANTS, CORROSION PREVENTION.

Belongs to a family of FLUID FILM products that are Environmentally Friendlier, solvent free, non-toxic, long lasting, thixotropic liquids that have been used for over fifty (50) years in the highly corrosive marine environment of ships and offshore drilling rigs. More recently they have been introduced and successfully utilized in the aerospace, aircraft and automobile industries as well as for home maintenance. Facilities where they are used include the following: Government facilities, commercial fishing concerns, gas companies, agriculture, salt plants, municipal plants, power plants, manufacturing plants and pulp and paper mills.

FOOD GRADE APPROVED

FLUID FILM "AS" & "NAS" are formulated from specially processed wool-wax, highly refined petroleum oils and selected agents to provide corrosion control, penetration, metal wetting and water displacement. These long lasting products contain no solvents, will not dry out and will penetrate through rust to the base metal, providing corrosion protection from both natural and industrial atmospheres. Heavily corroded and/or frozen parts such as nuts, bolts, shafts, etc., that would normally be damaged during maintenance, can be salvaged by applying FLUID FILM.

FLUID FILM AEROSOL "AS" AND NON-AEROSOL BULK "NAS", ENVIRONMENTALLY FRIENDLIER, SOLVENT FREE & NON-TOXIC.

PROPERTIES: (TYPICAL)

APPEARANCE:	Clear, straw colored liquid.
VISCOSITY:	300 centipoises @ 68°F
FLASH POINT, BULK LIQUID:	405°F (207°C) (COC) Minimum. ASTM-92) CLEVELAND OPEN CUP
NON-VOLATIVE:	89% minimum (3 hours @ 220°F)
SPECIFIC GRAVITY:	(NAS) 0.881 – 0.891
SPECIFIC CONDUCTIVITY:	Less than 10 ⁻⁹ mho/cm @ 1Hz.

FLUID FILM "AS" AEROSOL

EFFECT ON RUBBER: ASTM D-471 @+/- 158°F 70 hours	None on neoprene, buna-n and most synthetics. Some swelling on natural and butyl rubbers.
EFFECT ON PAINT:	None on most painted surfaces.
EFFECT ON ALUMINUM:	No pitting
EXTREME PRESSURE: ASTM D-2782 Timken Method	Fail load – 15 pounds
WEAR PREVENTION - CHARACTERISTICS: Four Ball Method	40 Kg., 1200 RPM for 1 hour @ 167°F. Results: Scar diameter of 0.49mm.
REPAINTABILITY:	CONTAINS NO SILICONES OR TEFLON. It is recommended that surfaces treated with FLUID FILM are hot water or steam detergent washed (120°F), whichever is most effective.
CORROSION PROTECTION: ASTM D-1735 Humidity Cabinet ASTM D-1748 Humidity Cabinet	Passes 50 days. Passes 30 days. Corrosion Requirement (Mil-C-16173, Grade 2 – Soft Films), passes 5%. Salt Fog, passes 1298 hours.
WATER REPLACEMENT:	Displaces water from all metal surfaces (Mil-C-23411, Paragraph 3.6)
TOXICITY:	Non-toxic, LD-50 greater than 3 grams per kilogram. Non-irritating skin Response. Very slight irritation to the eyes. (Toxicity tests preformed according to standard methods by an independent laboratory).
WARNING:	"AS": Extremely flammable. Contents under pressure. Do not puncture, Incinerate or store above 120°F. Keep from open flame. Combustible. Do not incinerate.
SPRAY NOZZLE CLEANING:	Turn can upside down, point in a safe direction and spray until only propellant escapes. If spray button becomes clogged during use, Pull it from the can and clean it with a fine wire or needle. Replace the button with a gentle twisting motion, keeping it pointed in a safe direction. Do not stick pins or other objects into nozzle tube.

KEEP OUT OF REACH OF CHILDREN.

**NLS Products Box 790, 1 Lakewood Crescent
Bobcaygeon, ON K0M 1A0**

Tel: (705) 738-2321 Fax: (705) 738-4550